

CHEMISTRY THAT MATTERS™

سابك
sabic

RELIABILITY+ INNOVATION

PIPE SYSTEM SOLUTIONS



SABIC GLOBAL PIPE PORTFOLIO

At SABIC we work closely with SABIC customers to continuously improve the performance of SABIC products to ensure that we meet the demands and expectations of customers. SABIC technical experts are available to offer you advice on your specific applications.

For more information please contact SABIC sales office in your region or visit our website to learn more about SABIC's portfolio: www.sabic.com

GLOBAL PIPE SEGMENT PORTFOLIO

MULTIMODAL HDPE

	Grades	Colour	Melt Mass-Flow Rate (g/10 min) MI2=190/2.16 MI5=190/5 MI21=190/21.6 ISO 1133	Density kg/m ³ ISO 1183	Typical Applications	Characteristics
HDPE	FJ01552	Natural	0.15 (MI2.16) 16 (MI21)	952	Irrigation pipes and tapes	Good processability
	P952	Natural	0.33 (MI5) 9 (MI21)	952	Non-Pressure pipe application, irrigation, cable ducts, corrugated & gravity pipes, sheets	Good processability
	P6006N	Natural	0.23 (MI5) 6.2 (MI21)	949	Potable & storm water, gas supply, sewage, corrugated and spiral systems, liner pipes	PE 4710, multi-modal, pressure pipes and good stress crack resistance (ESCR)
	P6006NA	Natural	0.23 (MI5) 6.2 (MI21)	949	Potable & storm water, gas supply, sewage, corrugated and spiral systems, liner pipes	PE 4710, multi-modal, pressure pipes and good stress crack resistance (ESCR)
	P4808N	Natural	0.23 (MI5) 6.5 (MI21)	949	Non-Pressure pipe application, irrigation, cable ducts, corrugated & gravity pipes, sheets	Multi-modal and good stress crack resistance (ESCR)
	P4808NA	Natural	0.23 (MI5) 6.5 (MI21)	949	Non-Pressure pipe application, irrigation, cable ducts, corrugated & gravity pipes, sheets	Multi-modal and good stress crack resistance (ESCR)
	P5305N	Natural	4.5 (MI21)	953	Non-Pressure pipe application, irrigation, cable ducts, corrugated & gravity pipes, sheets	Multi-modal and good stress crack resistance (ESCR)
	P5307N	Natural	8 (MI21)	952	Non-Pressure pipe application, irrigation, cable ducts, corrugated & gravity pipes, sheets	Multi-modal and good stress crack resistance (ESCR)
	P5616N	Natural	16 (MI21)	956	Non-Pressure pipe application, irrigation, cable ducts, corrugated & gravity pipes, sheets	Multi-modal and good stress crack resistance (ESCR)
	P4909NA	Natural	0.34 (MI5)	948	Non-Pressure pipe application, irrigation, cable ducts, corrugated & gravity pipes, sheets	Multi-modal and good stress crack resistance (ESCR)
HDPE PE100	Vestolen A 6060R	Black	0.3 (MI5)	959	Potable water, gas supply, sewage, cable ducts, casing pipe, steel rope sheathing, spiral pipes	PE 100, bimodal, pressure pipes and good stress crack resistance
	Vestolen A RELY 5922R	Black	0.2 (MI5)	959	Potable water, gas supply, sewage, spiral pipes, geothermal probes	PE 100RC, bimodal, pressure pipes, resistance to crack, trenchless installation, low sagging
	Vestolen A RELY 5923R	Black	0.2 (MI5)	959	Potable water, gas supply, sewage, spiral pipes	PE 100, bimodal, pressure pipes, low sagging
	Vestolen A RELY 5924R	Black	0.23 (MI5)	959	Potable, gas supply, sewage, spiral pipes	PE 100, bimodal, pressure pipes, low sagging
	Vestolen A RELY 5944HT	Black	0.2 (MI5)	959	High voltage cable protection, Industrial pipe, Geothermal pipes, district heating pipes	Class MRS10 MPa, bimodal, pressure pipes, high temperature resistance, low sagging, resistance to crack
	Vestolen A 5933RD	Black	0.2 (MI5)	959	Potable water, resistant to disinfectants	PE 100, bimodal, pressure pipes, high disinfectant resistance, resistance to crack, low sagging
	P6006	Black	0.23 (MI5) 6.2 (MI21)	959	Potable water, gas supply, sewage, corrugated and spiral pipes	PE 100, multi-modal, pressure pipes and good stress crack resistance
	P6006AO	Orange	0.23 (MI5) 6.3 (MI21)	950	Gas pressure pipes	Class MRS11.2 MPa; multi modal for pressure pipe applications, good stress crack resistance(ESCR)
	P6006AD	Black	0.23 (MI5) 6.4 (MI21)	959	Potable water, gas supply, sewage and other fluids	Class MRS 11.2 MPa; multimodal, especially designed for pressure pipes applications, good stress crack resistance (ESCR)
	P6006LS	Black	0.23 (MI5) 6.4 (MI21)	960	Potable water, gas supply, sewage and other fluids, useful for large diameter pipes and pressure pipes with low SDR	Class MRS 11.2 MPa; multimodal, low sagging
HDPE PE 80	5061R	Black	0.36 (MI5)	958	Potable water, gas supply, sewage, cable ducts, casing pipe, steel rope sheathing	PE 80, bimodal, pressure pipes and good stress crack resistance
HDPE PERTII	P4200RT	Natural	0.45 (MI5) 9.5 (MI21)	947	Domestic hot and cold water, Radiator connections, Metal pipe inner liners, secondary heating, oil and gas	Classified as PERT II as well as PE100, Good stress crack resistance combined with very good long term hydrostatic strength, high heat and high extraction stability

LLDPE

	Grades	Colour	Melt Mass-Flow Rate (g/10 min) MI2= 190 /2.16	Density kg/m3 ISO 1183	Typical Applications	Characteristics
LLDPE	128CNJ	Natural	1	928	Telecommunication cables, electrical conduits and drip & irrigation pipes	Combining stiffness, toughness, high melt strength with an excellent processability due to its broad molecular weight distribution
	P438J	Natural	0.4	938	Cylindrical and tap drip irrigation pipes	Excellent processability with a high level of consistency; exceptional mechanical properties and stress crack resistance

POLYPROPYLENE

	Grades	Colour	Melt Mass-Flow Rate (g/10 min) 230 / 2.16 ISO 1133	Density kg/m3 ISO 1183	Typical Applications	Characteristics
PP-Random Copolymer	Vestolen P9421 00901	Natural	0.3	898	Domestic hot and cold water, underfloor heating and cooling pipes	Natural, PP-R, high temperature resistance, long track records
	Vestolen P9421 66408	Green	0.3	898	Domestic hot and cold water, underfloor heating and cooling pipes	Green, PP-R, high temperature resistance, long track records
	Vestolen P9421 66409	Green	0.3	898	Domestic hot and cold water, underfloor heating and cooling pipes	Green, PP-R, high temperature resistance, long track records
	Vestolen P9421 66410	Green	0.3	898	Domestic hot and cold water, underfloor heating and cooling pipes	Green, PP-R, high temperature resistance, long track records
	Vestolen P9421 67727	Grey	0.3	898	Domestic hot and cold water, underfloor heating and cooling pipes, industrial pipes	Grey, PP-R, high temperature resistance, long track records
	XR19030E	Natural	0.3	905	Industrial sheets, industrial pipes, domestic sewage pipes	Good balance between stiffness and impact resistance, elevated heat stability, good processability. No stress whitening
	XR20036E	Natural	0.3	905	Industrial sheets, industrial pipes, domestic sewage pipes	Good impact resistance, elevated heat stability, good processability

POLYPROPYLENE

	Grades	Colour	Melt Mass-Flow Rate (g/10 min) 230 / 2.16 ISO 1133	Density kg/m3 ISO 1183	Typical Applications	Characteristics
PP-Homo Polymer	PP531Ph	Natural	0.3	905	Domestic sewage pipes, industrial sheets	High stiffness, elevated temperature resistance, good flowability
	PP535P	Natural	0.5	905	Domestic sewage pipes and fittings, industrial sheets	High stiffness, elevated temperature resistance, good flowability

POLYPROPYLENE

	Grades	Colour	Melt Mass-Flow Rate (g/10 min) 230 / 2.16 ISO 1133	Density kg/m ³ ISO 1183	Typical Applications	Characteristics
PP-Impact Copolymer	RELY 61EK61PS	Natural	0.3	905	Sewage & drainage pipes, manholes, corrugated pipes	Good balance between high cold impact resistance and high stiffness,
	RELY 71EK71PS	Natural	0.3	905	Sewage & drainage pipes, manholes, corrugated pipes	Good balance between high cold impact resistance and medium stiffness
	83EK10	Natural	1.2	905	Fittings & Manholes, corrugated pipes	Good impact strength and low flow properties
	83MF10	Natural	1.8	905	Fittings & Manholes	Good impact strength and moderate flow properties
	50EK75S	Natural	0.3	905	Sewage & drainage pipes, manholes	Good balance between stiffness and cold impact
	80EK20S	Natural	0.8	905	Fittings & Manholes	Good flowability and balance between impact and stiffness

PVC (Polyvinyl Chloride)

	Grades	K-Value	Typical Applications	Characteristics
PVC	67S	67	Pressure and non-pressure pipe profiles Corrugated tubes and conduits	Very low dust-level, high purity, high bulk density, narrow particle size distribution
	57S	57	Domestic sewage pipes and fittings, industrial sheets	Low content of fines, high tensile properties, narrow particle size distribution

PO COMPOUND

	Grades	Colour	Melt Mass-Flow Rate (g/10 min) MI2= 190 /2,16 MI5=190/5 MI21=190/21, 6 ISO 1133	Density kg/m ³	Typical Applications	Characteristics
Compound	G1620B	Natural	0.3 (230/2.16)	1030	Domestic hot and cold water	20% Glass fibers, for multi-layer pipe applications, good processability, reduced coefficient of thermal elongation
	P1600A	Natural	2.1 (MI5) 28.3 (MI21)	892	Inner layer for industrial and mining pipes	High abrasion resistance, good processability, and good compatibility with HDPE pipes
	19T1030	Natural	18.2 (230/2.16)	1160	Infiltration boxes, stormwater management	Mineral filled, high flow, high stiffness, heat stabilized

CONTACT US

Middle East and Africa

Global Headquarters

PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (011) 225 8000
F +966 (011) 225 9000
E info@sabic.com

Americas

2500 City West Boulevard
Suite 650, Houston
TX 77042
USA
T +1 713 532 4999
F +1 713 532 4994
E info@americas.sabic.com

Europe

PO Box 5151
6130 PD Sittard
The Netherlands
T +31 467 222 222
F +31 467 220 000
E info@sabic.com

Greater China

2550, Xiupu Road
Pudong Shanghai 201319, China
T +86 21 2037 8188
F +86 21 2037 8288
E stcl-sha@sabic.com.cn

Rest of Asia

One Temasek Avenue
06-01 Millenia Tower
Singapore 039192
T +65 655 725 55
F +65 653 181 01
E sappl@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right. SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.

© 2022 Copyright by SABIC. All rights reserved.